



# PRODUCT DATA SHEET

LC-E103

2-Part Flame Retardant  
Insert Potting Compound

### Description

LC-E103 is a two part, flame retardant, epoxy potting compound designed to have excellent adhesion to inserts and fasteners when placed within honeycomb sandwich structures.

### Advantages

The mixing and handling characteristics of LC-E103 make it an asset on the shop floor. Pre-packaged 6 oz. cartridges allow easy mixing and application through dispensing gun. Color coded Part A and Part B allow user to ensure thorough mixing. LC-E103 can be cured at room temperature or elevated temperatures for accelerated handling strength.

### Physical Properties & Mix Ratio

Density: 0.0477 (lbs/ft<sup>3</sup>)  
Part A: White paste  
Part B: Amber liquid  
Combined mixture: White paste  
Mix ratio by weight: 10:1

### Available Packaging

6 oz. injector kit cartridge (LC-E103/06C)  
1 gallon kit (8.3 lbs.) (LC-E103/1)  
Other packaging available upon request

### Pot/Shelf Life

Pot Life at Room Temperature: 70° F (21° C): 20 Minutes (6 oz. cartridge)  
Shelf Life @ Room Temperature: 70° F (21° C): 12 Months

**CAUTION: WHEN MIXING QUANTITIES IN EXCESS OF 250 GRAMS, USE CAUTION AS LARGER MIX QUANTITIES AND/OR EXCESSIVE MIX TIME CAN CAUSE AN INCREASED EXOTHERMIC (IE. VERY HOT) REACTION. THE USER IS ENCOURAGED TO DEVELOP STANDARD MIX PRACTICES.**

### Cure Cycle Recommendations

Handling Strength: 24 hours at Room temperature (70° F) (21° C)  
Full Strength Cure: 7 days at Room temperature (70° F) (21° C)

Mechanical Properties				
Property	Tested per Specification	-67° F	70° F	160° F
Hardness (Shore D)	ASTM D2240	N/A	81	N/A
Lap Shear (psi)	ASTM D1002-10	N/A	2500	N/A
Compression (psi)	ASTM D695	N/A	11000	N/A

LincolnCompositeMaterials.com      (714) 898-8350      Sales@LCMaterials.com

15422 Electronic Lane      Huntington Beach, CA 92649

Seller cannot anticipate all conditions under which seller's products, or the products of other manufacturers in combination with seller's products, may be used. Seller accepts no responsibility for results obtained by the application of seller's products or the safety and suitability of seller's products, either alone or in combination with other products. Users are advised to conduct their own tests to determine the safety and suitability of each such product or product combination for their own purposes. Unless otherwise agreed in writing, seller delivers the products without warranty of any nature, stated or implied, and buyers and users assume all responsibility and liability for loss or damage arising from the handling and use of said products, whether used alone or in combination with other products. Purchaser waives any claim against seller for direct, indirect, consequential or exemplary damages against seller, including without limitation, damage which may incur as a result of purchaser's use or misuse of the product or the product's failure to conform to any particular specification.