



# PRODUCT DATA SHEET

LC-E221

**250° Curing Flame  
Retardant Epoxy Film Adhesive**

## Description

LC-E221 is a 250°F (121°C) flame retardant epoxy film adhesive specifically designed for bonding metal to metal or metal to various core materials.

## Advantages

LC-E221 demonstrates excellent adhesion and toughness throughout various cure cycles using both press and vacuum bag curing. LC-E221 exhibits excellent resistant's to humidity as well as a variety of test fluids. LC-E221 can also be supplied both supported and unsupported in multiple weights and thicknesses. This material is self-extinguishing per FAR 25.853.

## Physical Properties

Density: 1.2 G/cm<sup>3</sup> per ASTM D792  
Gel Time @ 275°F (135°C): 4 -6 minutes  
Tg: 230°F (110°C)  
Color: Cream  
Tack: Medium

## Shelf Life/Out Life/Storage

Shelf Life: 6 months from Certification Date  
Out Life: 14 days @ 70°F (21°C)  
Storage Temp: 6 months @ 40° F or below

## Processing/Cure Cycle Recommendations

LC-E221 can be processed at temperatures from 235°F (113°C.) for 90 minutes to 290°F (143°C.) for 40 minutes. A 250°F (121°C) cure for 60 minutes is optimal in most cases using press, vacuum bag or autoclave.

Mechanical Properties				
Property	Tested per Specification	-67 °F	R.T. (75 °F)	180 °F
Tensile Shear (psi)	MMM-A-132	3900	4600	3500
Sandwich Peel Strength (inch lbs. / 1" width)	Mil-A-25463	11.2	15.1	15.3
Flatwise Tension (psi)	Mil-A-25463	1100	1300	900
Flexural Strength (lbs)	Mil-A-25463	2100	2400	2000

\*Tests performed using LC-E221M (supported) .060 psf, press cured @ at 250°F (121°C), 25 psi pressure.

LincolnCompositeMaterials.com

(714) 898-8350

Sales@LCMaterials.com

15422 Electronic Lane

Huntington Beach, CA 92649

Seller cannot anticipate all conditions under which seller's products, or the products of other manufacturers in combination with seller's products, may be used. Seller accepts no responsibility for results obtained by the application of seller's products or the safety and suitability of seller's products, either alone or in combination with other products. Users are advised to conduct their own tests to determine the safety and suitability of each such product or product combination for their own purposes. Unless otherwise agreed in writing, seller delivers the products without warranty of any nature, stated or implied, and buyers and users assume all responsibility and liability for loss or damage arising from the handling and use of said products, whether used alone or in combination with other products. Purchaser waives any claim against seller for direct, indirect, consequential or exemplary damages against seller, including without limitation, damage which may incur as a result of purchaser's use or misuse of the product or the product's failure to conform to any particular specification.

REV 170911