



PRODUCT DATA SHEET

LC-E334

350° Curing

Epoxy Glass Prepreg

Description

LC-E334 is a single or two side coated, 350°F (177°C) epoxy glass prepreg which exhibits excellent performance at temperatures up to 400°F (204°C). LC-E334 has proven to be ideal where a higher Tg is required along with additional toughness.

Advantages

LC-E334 is ideal for multi ply laminates or sandwich structures requiring an elevated Tg. Excellent strength and toughness allow for LC-E334 to perform well in a variety of finished part shapes and sizes. Low volatiles have also proven ideal for low void, multiple ply lay ups. A wide variety of cure cycles, cure temperatures and pressure also allow for LC-E334 to be very user friendly throughout processing.

Physical Properties

Density: 1.2 G/cm³ per ASTM D792
Gel Time @ 350°F (177°C): 3-5 minutes
Tg: 340°F (171°C)
Color: Cream
Tack: Medium-High

Shelf Life/Out Life/Storage

Shelf Life: 6 months from Certification Date
Out Life: 14 days @ 70°F (21°C)
Storage Temp: 40° F or below

Processing/Cure Cycle Recommendations

LC-E334 can be processed at 350°F (177°C.) for 90 minutes followed up with post cure of up to 400°F (204° C) when a higher Tg is required. A 350°F (177°C) cure for 90 minutes is optimal in most cases using press, vacuum bag or autoclave.

Mechanical Properties				
Property	Tested per Specification	R.T. (75 °F)	250° F	350 °F
Ultimate Tensile Strength (psi)	FTMS 406	66,100	62,300	60,000
Tensile Modulus (psi x 10E6)	FTMS 406	4.0	3.7	3.5
Ultimate Compression Strength (psi)	FTMS 406	67,500	53,000	46,000
Compression Modulus (psi x 10E6)	FTMS 406	4.1	3.9	3.6
Ultimate Flexural Strength (psi)	FTMS 406	92,000	77,500	64,000
Flexural Modulus (psi x 10E6)	FTMS 406	4.1	3.9	3.4

*Tests performed using LC-E334-7781 @ 40% RC, press cured @ at 350°F (177°C), 25 psi pressure.

**Additional fabric styles available upon request

LincolnCompositeMaterials.com

(714) 898-8350

Sales@LCMaterials.com

15422 Electronic Lane

Huntington Beach, CA 92649

Seller cannot anticipate all conditions under which seller's products, or the products of other manufacturers in combination with seller's products, may be used. Seller accepts no responsibility for results obtained by the application of seller's products or the safety and suitability of seller's products, either alone or in combination with other products. Users are advised to conduct their own tests to determine the safety and suitability of each such product or product combination for their own purposes. Unless otherwise agreed in writing, seller delivers the products without warranty of any nature, stated or implied, and buyers and users assume all responsibility and liability for loss or damage arising from the handling and use of said products, whether used alone or in combination with other products. Purchaser waives any claim against seller for direct, indirect, consequential or exemplary damages against seller, including without limitation, damage which may incur as a result of purchaser's use or misuse of the product or the product's failure to conform to any particular specification.