



PRODUCT DATA SHEET

LC-E426

250° Curing Flame

Retardant Epoxy Carbon Prepreg

Description

LC-E426 is a single or two side coated, 250°F (121°C) flame retardant epoxy carbon prepreg designed for a multitude of sandwich panel construction(s) as well as multiple ply laminates. This system can be used in a low tack version (press applications) or high tack and drape for complex contours and shapes.

Advantages

LC-E426 can be layered up using various core materials without the use of additional film adhesives. This system exhibits slightly better fire resistance than LC-E421. Excellent strength and toughness allow for LC-E426 to perform well in a variety of finished part shapes and sizes. Low volatiles have also proven ideal for low void, multiple ply lay ups. A wide variety of cure cycles, cure temperatures and pressure also allow for LC-E426 to be very user friendly throughout processing.

Physical Properties

Density: 1.45 G/cm³ per ASTM D792
Gel Time @ 275°F (135°C): 4-6 minutes
Tg: 218°F (103°C)
Color: Cream
Tack: Medium

Shelf Life/Out Life/Storage

Shelf Life: 6 months from Certification Date
Out Life: 14 days @ 70°F (21°C)
Storage Temp: 40° F or below

Processing/Cure Cycle Recommendations

LC-E426 can be processed at temperatures from 235°F (113°C.) for 90 minutes to 290°F (143°C.) for 40 minutes, using low, medium or high pressure. A 250°F (121°C) cure for 60 minutes is optimal in most cases using press, vacuum bag or autoclave processing.

Mechanical Properties				
Property	Tested per Specification	R.T. (75 °F)	R.T. Wet	160 °F
Ultimate Tensile Strength (psi)	FTMS 406	81,600	N/A	59,400
Tensile Modulus (PSI x 10E6)	FTMS 406	8.7	N/A	8.4
Ultimate Compression Strength (psi)	FTMS 406	73,300	N/A	61,800
Compression Modulus (PSI x 10E6)	FTMS 406	8.6	N/A	8.2
Ultimate Flexural Strength (psi)	FTMS 406	114,700	N/A	106,600
Flexural Modulus (PSI x 10E6)	FTMS 406	9.5	N/A	9.1
Horizontal Shear (psi)	FTMS 406	8400	N/A	N/A

Sandwich Properties				
Property	Tested per Specification	R.T. (75 °F)	N/A	N/A
Sandwich Peel Strength (in lbs/in)	FTMS 406	7	N/A	N/A
Flatwise Tensile Strength (psi)	FTMS 406	490	N/A	N/A

*Tests performed using 2 plies LC-E426-C100 @ 43% RC, press cured @ at 250° F, 25 psi pressure using ½” thick, 1/8” cell, 3# Nomex™ honeycomb core.

LincolnCompositeMaterials.com	(714) 898-8350	Sales@LCMaterials.com
15422 Electronic Lane	Huntington Beach, CA 92649	

Seller cannot anticipate all conditions under which seller's products, or the products of other manufacturers in combination with seller's products, may be used. Seller accepts no responsibility for results obtained by the application of seller's products or the safety and suitability of seller's products, either alone or in combination with other products. Users are advised to conduct their own tests to determine the safety and suitability of each such product or product combination for their own purposes. Unless otherwise agreed in writing, seller delivers the products without warranty of any nature, stated or implied, and buyers and users assume all responsibility and liability for loss or damage arising from the handling and use of said products, whether used alone or in combination with other products. Purchaser waives any claim against seller for direct, indirect, consequential or exemplary damages against seller, including without limitation, damage which may incur as a result of purchaser's use or misuse of the product or the product's failure to conform to any particular specification.