



PRODUCT DATA SHEET

LC-E101
2-Part Flame Retardant
Paste Adhesive

Description

LC-E101 is a two part flame retardant epoxy specifically designed for bonding various substrates, e.g., metallic, composite, etc. into finished shapes or structures.

Advantages

The mixing and handling characteristics make LC-E101 an asset on the shop floor. Pre-packaged 20 ounce cartridges allow easy mixing and application through dispensing gun. Color coded Part A and Part B allow user to ensure thorough mixing. LC-E101 can be cured at room temperature or elevated temperatures for accelerated handling strength.

Physical Properties & Mix Ratio

Density: 1.16 g/cm³ per ASTM D792
Part A: White paste
Part B: Cream paste
Combined mixture: White paste
Mix Ratio by weight: 2:1

Available Packaging

20 oz. Barrier kit cartridge (LC-E101/20C)
1 gallon kit (11.6 lbs.) (LC-E101/1)
5 gallon kit (58 lbs.) (LC-E101/5)
Other packaging available upon request

Pot/Shelf Life

Pot Life at Room Temperature: 70° F (21° C): 60 Minutes (500 grams mass)
Shelf Life @ Room Temperature: 70° F (21° C): 12 Months

CAUTION: WHEN MIXING QUANTITIES IN EXCESS OF 500 GRAMS, USE CAUTION AS LARGER MIX QUANTITIES AND/OR EXCESSIVE MIX TIME CAN CAUSE AN INCREASED EXOTHERMIC (IE. VERY HOT) REACTION. THE USER IS ENCOURAGED TO DEVELOP STANDARD MIX PRACTICES.

Cure Cycle Recommendations

Handling Strength: 4 hours at Room temperature (70° F) (21° C)
Accelerated Handling Strength: 120 minutes at 150° F (65° C)

Full Strength/Cure: 7 Days at Room temperature (70° F) (21° C)

Mechanical Properties

Property	Tested per Specification	-67° F	70° F	160° F
Hardness (Shore D)	ASTM D2240	N/A	80	N/A
Lap Shear (psi)	ASTM D1002-10	N/A	3300	2200
Lap Shear (psi) (14 Day Conditioning @ 160° F/ 95% RH)	ASTM D1002-10	N/A	3300	N/A
Compression (psi)	ASTM D695	N/A	7400	N/A
Work /Pot Life (After 60 minutes from blending) Shear Strength (psi)	ASTM D1002-10	N/A	3000	N/A

LincolnCompositeMat

15422

Seller cannot anticipate all conditions under which seller's products, or the products of other manufacturers in combination with seller's products, may be used. Seller accepts no responsibility for results obtained by the application of seller's products or the safety and suitability of seller's products, either alone or in combination with other products. Users are advised to conduct their own tests to determine the safety and suitability of each such product or product combination for their own purposes. Unless otherwise agreed in writing, seller delivers the products without warranty of any nature, stated or implied, and buyers and users assume all responsibility and liability for loss or damage arising from the handling and use of said products, whether used alone or in combination with other products. Purchaser waives any claim against seller for direct, indirect, consequential or exemplary damages against seller, including without limitation, damage which may incur as a result of purchaser's use or misuse of the product or the product's failure to conform to any particular specification.